

# USG DUROCK™ BRAND ULTRACAP® SELF-LEVELING UNDERLAYMENT

Technical Data	USG Durock™ Brand UltraCap® Self-Leveling Underlayment¹	Drytek® Levelex™ Self-Leveling Underlayment²
<b>Manufacturer</b>	USG	Laticrete®
<b>Composition</b>	Portland cement	Cement blend
<b>Thickness</b>	Featheredge to 2 in. (50.8 mm) neat, up to 5 in. (127 mm) when extended	1/8 in. to 3 in. (3 to 76 mm)
<b>Compressive Strength per ASTM C109 (Modified)</b>	5,000 psi (35.4 MPa) at 28 days	4,000 psi (27.6 MPa) at 28 days
<b>Flow Time</b>	15-20 min. at 70 °F (21 °C)	20-30 min.
<b>Walkable</b>	2-4 hours (after set)	3-4 hours
<b>Finish Floor Application³</b>	2-3 days	Within 3 days
<b>Final Usage</b>	Underlayment and wear surface with proper coating	Underlayment only
<b>Self-Leveling</b>	Yes	Yes

Surface Preparation	USG Durock™ Brand UltraCap® Self-Leveling Underlayment¹	Drytek® Levelex™ Self-Leveling Underlayment²
<b>Concrete Slab Cure Minimum</b>	28 days	28 days
<b>Structurally Sound</b>	Yes	Yes
<b>Building Enclosed</b>	Yes	Yes
<b>Minimum Maintained Temperature</b>	50 °F (10 °C)	50 °F (10 °C)
<b>Dry and Clean – Remove Mud, Oil, Grease and Other Contaminating Factors</b>	Yes	Yes
<b>Shot Blasting or Scarified</b>	Yes	Yes
<b>CDPH (CA section 01350) Compliant</b>	Yes	N/A
<b>Website</b>	usg.com	drytek.com

**PRODUCT INFORMATION**

See usg.com for the most up-to-date product information.

**TRADEMARKS**

The trademarks USG, DUROCK, ULTRACAP, IT'S YOUR WORLD. BUILD IT., the USG logo, the design elements and colors, and related marks are trademarks of USG Corporation or its affiliates.

Drytek, Laticrete and Levelex are trademarks of Laticrete International, Inc.

**NOTE**

Products described here may not be available in all geographic markets. The information in this document is subject to change without notice. USG Corp. assumes no responsibility for any errors that may inadvertently appear in this document. Consult your USG Company sales office or representative for information.

**NOTICE**

We shall not be liable for incidental or consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instruction or for other than the intended use. Our liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing to us within thirty (30) days from date it was or reasonably should have been discovered.

**SAFETY FIRST!**

Follow good safety/industrial hygiene practices during installation. Wear appropriate personal protective equipment. Read SDS and literature before specification and installation.

**NOTES:**

1. Data taken from *USG Durock™ Brand UltraCap® Self-Leveling Underlayment Submittal* (CB575/rev. 7-15).
2. Competitive data taken from Drytek® Levelex™ technical data sheet DS-076.1-0615 and TDS 230D *Drytek Substrate Preparation and Primer Guide*.
3. Dependent on underlayment thickness and drying conditions.

800 USG.4YOU  
800 (874.4968)  
usg.com

United States Gypsum Company  
550 West Adams Street  
Chicago, IL 60661

CB810-USA-ENG/8-16  
© 2016 USG Corporation and/or its affiliates. All rights reserved.  
Printed in U.S.A.