



Compagnie Henry Canada, Inc.  
10, avenue St-Pierre  
Lachine QC H8R 1N7  
Canada



(514) 364-5224  
1 (800) 361-4599  
Télec/Fax : (514) 364-7270  
www.bakor.com  
www.henry.com

March 10, 2009

Dan Collins  
USG

**Subject: Blueskin SA Compatibility with USG Securock Glass-Mat Sheathing**

Mr. Collins,

Based on testing where Blueskin SA was applied to USG Securock Glass-Mat Sheathing, we are confirming that the vapour barrier membrane is compatible with the sheathing substrate provided a primer, namely Blueskin Primer, is applied following the recommended procedure. The bond strength of membrane to substrate was measured to be 6.1 lbs/in width after 5 days set time and remained stable for some time following. We consider this to be a typical value representing excellent bonding characteristics.

Please note that our water based primer, Aquatac proved to offer markedly less bond strength and is not recommended as a suitable primer.

Best regards,

Shawn Melançon  
Henry Company Canada  
Scarborough Technical Center  
R&D Department

CC: Dusan Subotic: Technical Director  
Peter Saunders: Technical Sales Representative