



Compagnie Henry Canada, Inc.  
 10, avenue St-Pierre  
 Lachine QC H8R 1N7  
 Canada



(514) 364-5224  
 1 (800) 361-4599  
 Téléc/Fax : (514) 364-7270  
[www.bakor.com](http://www.bakor.com)  
[www.henry.com](http://www.henry.com)

August 28, 2009

Dan Collins  
USG

**Subject: Air Barrier Compatibility with USG Securock Glass-Mat Sheathing**

Mr. Collins,

Based on testing where several permeable and non-permeable liquid applied air barriers applied to USG Securock Glass-Mat Sheathing, we are confirming that the vapour barrier membranes are compatible with the sheathing substrate; no primer is required for all listed membranes. The bond strength of membranes are summarized in the table below, adhesion was tested after 14 days of cure time at 22-25 C and a relative humidity of 55%

Air Barrier	Permeability	Bond Strength
Air Bloc 06	Non permeable	Excellent
Air Bloc 07	Permeable	Very good
Air Bloc 21	Non permeable	Excellent
Air Bloc 31	Permeable	Very good
Air Bloc 32	Non permeable	Very good
Air Bloc 33	Permeable	Excellent

Should you require additional information, please do not hesitate to contact me at 416 724-2000 ext 236

Best regards,

Shawn Melançon  
 Henry Company Canada  
 Scarborough Technical Center  
 R&D Department

CC: Dusan Subotic: Technical Director  
 Peter Saunders: Technical Sales Representative