



Friday, February 13, 2009

Attn: Dan Collins  
SHEETROCK Brand Products & Systems Manager

RE: Securock Glass-Mat Sheathing Adhesion Testing

Tracking #: 605P93

Dear Mr. Collins:

Upon your request, the Technical Service Group has evaluated the Peel Adhesion properties of Pecora AC-20 Acrylic Latex & 864NST Silicone Sealants on the substrate provided. This testing was performed in accordance with ASTM C-794. The following results were obtained:

**Peel Adhesion Testing (ASTM C-794)**

**Substrate:** Securock Glass-Mat Sheathing – Green surface  
**Sealant:** Pecora AC-20  
**Primer:** None required  
**Surface Preparation:** Isopropyl wipe, two-cloth method  
**Results:** **Pass – dry adhesion only<sup>1</sup>**

**Substrate:** Securock Glass-Mat Sheathing – Green surface  
**Sealant:** Pecora 864NST  
**Primer:** None required  
**Surface Preparation:** Isopropyl wipe, two-cloth method  
**Results:** **Pass – dry adhesion only<sup>1</sup>**

<sup>1</sup> Approved for temporary weatherseal only

Should you have any questions concerning the test methods employed or the results reported here please do not hesitate to call us.

Sincerely,

A handwritten signature in black ink that reads 'Michael D. Murphy'.

Michael D. Murphy  
Technical Service Representative

A handwritten signature in black ink that reads 'Roy D. Cannon, Jr.'.

Roy D. Cannon, Jr.  
Director of Technical Service