

# USG HYDROCAL® BRAND WHITE GYPSUM CEMENT SOUTHARD, OK

## DESCRIPTION

USG Hydrocal® Brand White Gypsum Cement is a good multi-purpose product for people looking to upgrade from a standard plaster product to one that has a higher degree of hardness and impact resistance. USG Hydrocal White Gypsum Cement is designed for solid and hollow casting and is ideal for giftware and lamp base applications. USG Hydrocal White Gypsum Cement is compatible with numerous color pigments. If information for a specific use is needed, please contact your local USG Sales Representative for further assistance.

## TYPICAL PHYSICAL PROPERTIES

Normal Consistency	40 - 45 lbs. water/100 lbs. product (18 - 20 kg water/45 kg product)
Hand Mix Vicat Set, Target	20 - 30 minutes
Compressive Strength, One Hour After Set	3000 psi (20.7 MPa)
Compressive Strength, Dry	6000 psi (41.4 MPa)
Density, Wet	110 lbs./cu. ft. (1762 kg/m <sup>3</sup> )
Density, Dry	90 lbs./cu. ft. (1442 kg/m <sup>3</sup> )
% Maximum Expansion	0.42%

**NOTE** The *Typical Physical Properties* in the above table were achieved under controlled laboratory conditions with freshly produced material, results may vary. Other set times may be available; call your USG Sales Representative for more information. Hand mix times will be longer.

## MIXING INSTRUCTIONS

### MIX PREPARATION

Use potable water at temperatures between 70 °F (21 °C) and 100 °F (38 °C). Because variations in slurry (USG Hydrocal White Gypsum Cement and water mixture) temperature produce variations in set time, it is important to keep both the USG Hydrocal White Gypsum Cement and water in a stable temperature environment prior to use. The higher the temperature of the slurry, the shorter the set time. Conversely, the lower the temperature of the slurry, the longer the set time.

Weigh both the USG Hydrocal White Gypsum Cement and the water prior to use for each mix. The water-to-USG Hydrocal White Gypsum Cement ratio is critical because it governs the strength and the density of the final cast.

### SOAKING

Sift or strew USG Hydrocal White Gypsum Cement into the water slowly and evenly. Do not drop large amounts of USG Hydrocal White Gypsum Cement directly into the water as proper soaking of the USG Hydrocal White Gypsum Cement may not occur. USG Hydrocal White Gypsum Cement should be fully dispersed in the water prior to mixing. Small batches require less soaking time than large batches. See USG IG503 *Plaster Mixing Procedures* for specific soaking instructions.

### MIXING

Mixing USG Hydrocal White Gypsum Cement slurry is one of the most important steps in producing USG Hydrocal White Gypsum Cement casts with maximum strength, absorption, hardness and other important properties.

Mechanically mixed slurries develop uniform casts with optimal strengths. USG Hydrocal White Gypsum Cement can be mechanically mixed through both batch and continuous processes. Proper blade and bucket dimensions are important for obtaining the best batch mix (see USG IG503 *Plaster Mixing Procedures* for details).

Longer mixing times result in higher mold strength and shorter set times.

## POURING

To prevent air entrainment and provide a uniform, smooth surface, careful pouring of USG Hydrocal White Gypsum Cement slurry is necessary. Agitation of the filled mold is a further step used to prevent air at or near the mold surface. Whenever possible, USG Hydrocal White Gypsum Cement slurry should be poured carefully in the deepest area so that the slurry flows evenly across the surface of the case mold.

Pouring a large amount of slurry directly on the face of the case mold may result in slight densification of the USG Hydrocal White Gypsum Cement mold at the point where it strikes the surface of the case. This produces a hard spot, giving uneven absorption.

---

## DRYING

All casts should be dried as quickly as is safely possible after manufacture so that maximum physical properties can develop. Dry to a constant weight.

The best drying rooms or ovens provide 1) uniform and rapid circulation (minimum of 15-30 fps (4.6-9.1 mps)) of air with no "dead spots" having little or no air movement, 2) equal temperatures throughout the entire area, and 3) provisions for exhausting a portion of the air while replacing it with fresh air. High humidity surrounding the drying room or oven inhibits drying efficiency because the air pulled into the room is incapable of picking up much moisture from the molds.

The maximum temperature at which USG Hydrocal White Gypsum Cement molds are safe from calcination is 120 °F (49 °C). With substantial free water in the mold, a higher drying temperature can be used without difficulty. As drying progresses, the temperature must be reduced to prevent calcination. Before removing molds from the dryer, the temperature should approach that of the area around the dryer to prevent thermal shock. See IG502 *Drying Plaster Casts* for additional information.

---

## STORAGE AND USE

When properly used, USG Hydrocal White Gypsum Cement is easy to work with and complies with the federal Labeling of Hazardous Art Materials Act, 12 U.S.C. Section 1277 and ASTM D4236. Keep indoors at temperatures between 65 °F - 75 °F (18 °C - 24 °C) and 45% - 55% RH. Do not stack more than two pallets high. Keep from drafts. Rotate stock. USG Hydrocal White Gypsum Cement should be used within 6 months of the manufacturing date located on the package. Always follow handling and use directions and safety warnings on the package.

### PRODUCT INFORMATION

See [usg.com](http://usg.com) for the most up-to-date product information.

### CAUTION

When mixed with water, this material hardens and becomes very hot sometimes quickly. DO NOT attempt to make a cast enclosing any part of the body using this material. Dust from mixing may cause irritation to eyes, skin, nose, throat and upper respiratory tract. Use only in a well-ventilated area, wear a NIOSH/MSHA-approved respirator. Wear eye protection. If eye contact occurs, flush thoroughly with water for 15 minutes. If on skin: Wash with plenty of water. If swallowed and/or irritation persists, call physician. For more information call Product Safety: 800-507-8899 or see the SDS at [usg.com](http://usg.com)

**KEEP OUT OF REACH OF CHILDREN.**

### TRADEMARKS

The trademarks USG, HYDROCAL, IT'S YOUR WORLD, BUILD IT., the USG logo, the design elements and colors and related marks are trademarks of USG Corporation or its affiliates.

### NOTE

The information in this document is subject to change without notice. USG Corp. and/or its affiliates assume no responsibility for any errors that may inadvertently appear in this document. Consult your USG sales office or representative for information.

### NOTICE

We shall not be liable for consequential, incidental or special damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instructions or for other than the intended use. Our liability is expressly limited to the replacement of defective goods or a refund of the purchase price, at USG's option, and does not include costs of labor or any other costs associated with material replacement. Any claim shall be deemed waived unless made in writing to us within thirty (30) days from date it was or reasonably should have been discovered.

### SAFETY FIRST!

Follow good safety/industrial hygiene practices during installation. Wear appropriate personal protective equipment. Read applicable SDSs and literature before specification and installation.

800 USG.4YOU  
800 (874.4968)  
[usg.com](http://usg.com)

Manufactured by  
United States Gypsum Company  
550 West Adams Street  
Chicago, IL 60661

IG1381-USA-ENG/rev. 11-19  
© 2019 USG Corporation and/or  
its affiliates. All rights reserved.  
Printed in U.S.A.

**USG**  
IT'S YOUR WORLD. BUILD IT.® 