

Levelrock® Floor Underlayment 2500 Pre-Sanded



Premium poured floor underlayment

- Fast application, fast-setting allows return of trade traffic within hours
- Pre-sanded for consistent quality
- Industry's most economical, highest compressive strength in class
- Ideal for barrel-mixing and small area applications
- Smooth, crack-resistant surface
- Can be used for leveling “duck ponds” on concrete decks in high rise construction
- Applied by USG LEVELROCK authorized applicators

Description

LEVELROCK® 2500 pre-sanded floor underlayment is a high-quality, pre-sanded cementitious floor underlayment designed by USG for interior use in multi-family, light-commercial and wood-framed construction. It is formulated to provide typical compressive strengths from 2500 psi to 3500 psi at a 3/4-in. minimum thickness.

USG poured cementitious floor underlayment systems provide an economical way to achieve lightweight, fire-resistant, sound-rated, smooth and monolithic floors in residential and light-commercial construction. Typical applications are for areas over construction systems already having a fire rating. Designed sound systems provide for improved STC and IIC ratings when used with LEVELROCK sound attenuation products.

Limitations

1. Do not use in exterior applications.
2. Do not use as a wearing surface.
3. Do not install where continuous exposure to moisture is a possibility (for instance, exterior balconies or large commercial/institutional shower rooms).
4. Do not install in below-grade applications. Contact USG for on-grade application recommendations.
5. Install only on tongue-and-groove edge plywood or OSB, or square-edge wood subfloor with back-bracing.
6. Structure shall be designed so that deflection does not exceed L/360 live or dead load. Certain floor coverings such as marble, limestone, travertine and wood may have more restrictive deflection limits. Consult the appropriate floor covering manufacturer.
7. Do not use as a structural element.

Installation

During the entire installation process, the building must be enclosed and temperature maintained at a 50 °F minimum until permanent heating is available. Adequate ventilation must be provided to ensure uniform drying of the installed floor underlayment, which typically occurs within 5 to 7 days at a ¾ in. thickness. Protect floors from heavy trade traffic loads (i.e. loaded drywall carts, heavy tool cabinets, etc.) with plywood. The application of LEVELROCK™ floor underlayment primer to the subfloor is necessary to provide maximum bond between the underlayment and subfloor.

Concrete subfloors receiving cementitious underlayment systems must be cured properly (generally for a minimum of 28 days) prior to the underlayment installation. For on- or above-grade applications on concrete subfloors or concrete planks, measure the Moisture Vapor Emission Rate (MVER) using ASTM F1869. MVER should be below 5 lbs./1000 sq. ft./24 hrs. Contact USG for further information. Concrete subfloors should be treated properly with LEVELROCK™ floor underlayment concrete primer, according to USG recommendations. Refer to *LEVELROCK Floor Underlayment Finished Floor Installation Guidelines* (IG1457) for floor-covering installation.

For further details on installation requirements, specifications and the most up-to-date product information, please see levelrock.com.

Product Data

LEVELROCK 2500 pre-sanded floor underlayment is sanded at the factory. Job site addition of sand is not recommended and will void the warranty. LEVELROCK 2500 pre-sanded floor underlayment is mixed with water to yield a lightweight slurry for a smooth, monolithic surface. A 3/4-in. thick underlayment weighs approximately 7.5 lbs./sq. ft. and has an approximate dry density range of 116–124 lbs./cu. ft.

Approximate Compressive Strength (aggregated) ASTM C472 (modified): 2500-3500 psi*

Approximate Dry Density (aggregated): 116–124 lbs./cu. ft.

Note *Compressive strengths published herein were achieved under controlled laboratory conditions. Actual field results may differ due to environmental conditions; inconsistent proportioning of field applied water and LEVELROCK floor underlayment, as well as differences in mixing/pumping equipment.

Test Data

Sound

USG has conducted a variety of sound tests on underlayment systems at NVLAP-accredited laboratories. These tests have been in conformance with ASTM E90 and E492. Consult USG publications IG1650 and SA305 for STC and IIC results on a variety of floor coverings meeting current code requirements.

UL Designs

Contact your USG representative.

Submittal Approvals

Job Name	
Contractor	Date

Product Information

See levelrock.com for the most up-to-date product information.

WARNING!

When mixed with water, this material hardens and becomes very hot – sometimes quickly. DO NOT attempt to make a cast enclosing any part of the body using this material. Failure to follow these instructions can cause severe burns that may require surgical removal of affected tissue or amputation of limb. Portland cement is strongly alkaline. Direct contact can be corrosive and cause severe damage or chemical burns to the eyes and wet or moist skin. Avoid contact with eyes and skin. Wear eye protection, alkali-resistant protective gloves, long-sleeved shirts and pants to prevent

direct contact. If eye contact occurs, immediately flush thoroughly with water for 30 minutes and seek medical advice. Inhalation of dust may be corrosive or cause chemical burns or irritation to nose, throat and respiratory tract. Long-term breathing of respirable crystalline silica dust can cause permanent lung damage and/or cancer. Avoid breathing dust. Use in a well-ventilated area or provide sufficient local ventilation. If dusty, wear a NIOSH/MSHA-approved dust respirator. Wash thoroughly with soap and water after use. Do not ingest. If ingested, call physician. Product safety information: 800 507.8899 or usg.com. **KEEP OUT OF REACH OF CHILDREN.**

Trademarks

The following trademarks used herein are owned by United States Gypsum Company or a related company: LEVELROCK, USG, USG in stylized letters.

Notice

We shall not be liable for incidental or consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instruction or for other than the intended use. Our liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing to us within thirty (30) days from date it was or reasonably should have been discovered.

Safety First!

Follow good safety/industrial hygiene practices during installation. Wear appropriate personal protective equipment. Read MSDS and literature before specification and installation.

