

# USG DUROCK™ BRAND QUIK-COVER™ SELF-LEVELING UNDERLAYMENT

Technical Data	USG Durock™ Brand Quik-Cover™ Self-Leveling Underlayment <sup>1</sup>	Schonox® ZM Rapid <sup>2</sup>
<b>Composition</b>	Calcium aluminate cement	Cement, Portland blend
<b>Thickness</b>	Featheredge to 1 in. (25.4 mm)	1/16 in. - 3/8 in. (1.6 - 9.5 mm), up to 1 in. (25.4 mm) with aggregate
<b>Compressive Strength</b>	5000 psi (34.5 MPa)	7550 psi (50 N/mm <sup>2</sup> )
<b>Mixing Time</b>	1-3 minutes	3 minutes
<b>Flow Time<sup>3</sup> at 70 °F (21 °C)</b>	20 minutes	25 minutes
<b>Walkable<sup>3</sup></b>	60-90 minutes	1-1.5 hours
<b>Finish Floor Application<sup>3</sup></b>	1 hour, wood in 12 hours	1.5-2 hours at 3/8 in. (9.5 mm), wood in 12 hours
<b>Final Usage</b>	Underlayment and wear surface with proper coating	Underlayment and wear surface
<b>Coverage</b>	25 sq. ft. (2.3 m <sup>2</sup> ) at 1/4 in. (6 mm) per 50 lb. (22.7 kg) bag	60-70 sq. ft. (5.6-6.5 m <sup>2</sup> ) at 1/8 in. (3 mm) per 55 lb. (24.9 kg) bag
<b>Self-Leveling</b>	Yes	Yes
<b>Website</b>	usg.com	hpsubfloors.com

Surface Preparation	USG Durock™ Brand Quik-Cover™ Self-Leveling Underlayment <sup>1</sup>	Schonox® ZM Rapid <sup>2</sup>
<b>Concrete Slab Cure Minimum</b>	28 Days	N/A
<b>Building Enclosed</b>	Yes	Yes
<b>Remove Mud, Oil, Grease and Other Contaminating Factors</b>	Yes	Yes
<b>Shot Blasting or Scarification</b>	No mechanical floor preparation required for most applications	Mechanically clean, if necessary

#### PRODUCT INFORMATION

See usg.com for the most up-to-date product information.

#### TRADEMARKS

The trademarks USG, DUROCK, QUIK-COVER, IT'S YOUR WORLD. BUILD IT., the USG logo, the design elements and colors, and related marks are trademarks of USG Corporation or its affiliates. Schonox is a trademark of HPS North America, Inc.

#### NOTE

The information in this document is subject to change without notice. USG Corp. assumes no responsibility for any errors that may inadvertently appear in this document. Consult your USG Company sales office or representative for information.

#### NOTICE

We shall not be liable for incidental or consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instruction or for other than the intended use. Our liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing to us within thirty (30) days from date it was or reasonably should have been discovered.

#### SAFETY FIRST!

Follow good safety/industrial hygiene practices during installation. Wear appropriate personal protective equipment. Read SDS and literature before specification and installation.

#### NOTES:

1. Data taken from *USG Durock™ Brand Quik-Cover™ Self-Leveling Underlayment Submittal* (CB844/4-17).
2. Competitive product data taken from Schonox ZM Rapid Product Data Sheet B\_0346us\_17-01.
3. Warmer temperatures can decrease working/dry time, and cooler temperatures and high humidity can increase working/dry time on both products.

800 USG.4YOU  
800 (874.4968)  
usg.com

United States Gypsum Company  
550 West Adams Street  
Chicago, IL 60661

CB5017-USA-ENG/6-17  
© 2017 USG Corporation and/or its affiliates. All rights reserved.  
Printed in U.S.A.