

USG DUROCK™ BRAND QUIK-COVER™ SELF-LEVELING UNDERLAYMENT

Technical Data	USG Durock™ Brand Quik-Cover™ Self-Leveling Underlayment ¹	UZIN NC 172 BiTurbo ²
Composition	Calcium aluminate cement	Portland blend
Thickness	Featheredge to 1 in. (25.4 mm)	1/8 in.- 1/2 in. (3.2 - 12.7 mm), special instructions for deeper pours
Compressive Strength	5000 psi (34.5 MPa)	7550 psi (52.1 MPa)
Mixing Time	1-3 minutes	1 minute
Flow Time³ at 70 °F (21 °C)	20 minutes	15 minutes
Walkable³	60-90 minutes	1 hour
Finish Floor Application³	1 hour, wood in 12 hours	1 hour, wood in 12 hours, natural stone in 24 hours
Final Usage	Underlayment and wear surface with proper coating	Underlayment and wear surface
Coverage	25 sq. ft. (2.3 m ²) at 1/4 in. (6 mm)	30 sq. ft. (2.78 m ²) at 1/4 in. (6 mm)
Self-Leveling	Yes	Yes
Website	usg.com	uzin.us

Surface Preparation	USG Durock™ Brand Quik-Cover™ Self-Leveling Underlayment ¹	UZIN NC 172 BiTurbo ²
Concrete Slab Cure Minimum	28 Days	N/A
Building Enclosed	Yes	Yes
Remove Mud, Oil, Grease and Other Contaminating Factors	Yes	Yes
Shot Blasting or Scarification	No mechanical floor preparation required for most applications	No mechanical floor preparation required for most applications

NOTES:

1. Data taken from *USG Durock™ Brand Quik-Cover™ Self-Leveling Underlayment Submittal* (CB844/4-17).
2. Competitive product data taken from UZIN NC 172 Bi-Turbo Product Data Sheet 04.17MSL.
3. Warmer temperatures can decrease working/dry time, and cooler temperatures and high humidity can increase working/dry time on both products.

PRODUCT INFORMATION

See usg.com for the most up-to-date product information.

TRADEMARKS

The trademarks USG, DUROCK, QUIK-COVER, IT'S YOUR WORLD. BUILD IT., the USG logo, the design elements and colors, and related marks are trademarks of USG Corporation or its affiliates.

UZIN is a trademark of Uzin Utz Aktiengesellschaft Corporation.

NOTE

The information in this document is subject to change without notice. USG Corp. assumes no responsibility for any errors that may inadvertently appear in this document. Consult your USG Company sales office or representative for information.

NOTICE

We shall not be liable for incidental or consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instruction or for other than the intended use. Our liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing to us within thirty (30) days from date it was or reasonably should have been discovered.

SAFETY FIRST!

Follow good safety/industrial hygiene practices during installation. Wear appropriate personal protective equipment. Read SDS and literature before specification and installation.

800 USG.4YOU
800 (874.4968)
usg.com

United States Gypsum Company
550 West Adams Street
Chicago, IL 60661

CB5018-USA-ENG/6-17
© 2017 USG Corporation and/or its affiliates. All rights reserved.
Printed in U.S.A.