

USG LEVELROCK® BRAND FLOOR UNDERLAYMENT

3500

3500 GREEN

Premium engineered cementitious underlayments

- Fast application, fast-setting allows for return of light trade traffic within hours
 - Ideal for wood frame, renovation, hotel/motel and light-commercial construction
 - Meets vinyl industry commercial performance requirements
 - UL designs available up to 2-hour fire rating
 - Smooth, crack resistant surface
 - Helps maximize sound isolation between floors/units
 - USG Levelrock 3500 Green floor underlayment may assist in obtaining LEED® credits
 - Applied by USG Levelrock authorized applicators
-

DESCRIPTION

USG Levelrock® Brand 3500 and USG Levelrock® 3500 Green floor underlayment are high-quality, versatile engineered cementitious underlayments for indoor use in light-commercial and renovation construction. They can be easily applied over wood and concrete subfloors at a thickness of up to 3 in. Their high compressive strengths at low thicknesses provide superior underlayment performance for higher-traffic areas and minimize floor damage from trades. High production rates, lightweight with high compressive strength and fire resistance make USG Levelrock 3500 and 3500 Green floor underlayments ideal alternatives to lightweight concrete floor applications.

USG Levelrock 3500 Green floor underlayment is made with recaptured gypsum, from the flue gas desulfurization of the process used to clean combustion gases from fossil-fuel-burning power plants. This process is used to greatly reduce emissions of sulfur dioxide which helps the environment by reduction of harmful acid rain. The use of this recaptured gypsum also eliminates the need to dispose of the material in landfills as a solid waste. In addition, the high recycled content of USG Levelrock 3500 Green floor underlayment may assist in obtaining LEED credits 4.1 and 4.2, while both USG Levelrock 3500 and 3500 Green floor underlayment may assist in obtaining LEED credits 5.1 and 5.2.

USG engineered cementitious underlayments are mixed with sand and water at the job site to yield a lightweight underlayment with a smooth and monolithic surface. A ¾-in. thick underlayment weighs approximately 7.5 lbs./sq. ft. and has an approximate dry density range of 118-124 lbs./cu. ft.

USG engineered cementitious underlayment systems provide an economical way to achieve lightweight, fire-resistant, sound-rated, smooth and monolithic floors in residential and light-commercial construction. When used with USG Levelrock™ Perimeter Isolation Strip, USG Levelrock 3500 and 3500 Green floor underlayment provide an enhanced system to reduce potential cracking. Typical applications are less labor intensive than many other types of construction and provide high fire ratings. Designed sound systems provide for improved STC and IIC ratings when used with USG Levelrock™ sound attenuation products.

WARRANTY

A 10-year limited system warranty applies when using USG Levelrock 3500 and 3500 Green engineered cementitious underlayments sealed with USG Durock™ X2 primer-sealer and a XL Brands® manufactured adhesive. Please contact USG for further details.

LIMITATIONS

1. Do not use in exterior applications.
2. Do not use as a wear surface.
3. Do not install where continuous exposure to moisture is a possibility.
4. Do not install in below-grade applications. Contact USG for on-grade application recommendations.
5. For wood subfloors, install only on tongue-and-groove edge plywood or OSB, or square-edge wood subfloor with back-bracing.
6. Do not use over expansion or isolation joints. Continue all movement joints in the concrete slab up through the layer of underlayment. In areas where the expansion or isolation joints are not present in the floor or where the concrete slab has developed systematic cracks in response to slab movement, consult with an engineer on the project or request the services of a professional structural engineer to provide such joints as part of the system in accordance with engineering requirements and industry standards.
7. Structure shall be designed so that deflection does not exceed L/240 from combined dead and live loads and L/360 from live loads. Certain floor coverings such as marble, limestone, travertine and wood may have more restrictive deflection limits. Consult the appropriate floor-covering manufacturer.

INSTALLATION

During the entire installation process, the building must be enclosed and temperature maintained at a 50 °F minimum until permanent heating is available. Adequate ventilation must be provided to ensure uniform drying of the installed floor underlayment, which typically occurs within 5 to 7 days at a ¾ in. thickness. Protect floors from heavy trade traffic loads (i.e. loaded drywall carts, heavy tool cabinets, etc.) with plywood. This may cause the protected areas to take longer to dry. Check for dryness in these areas before installing floor covering. For applications over plywood or oriented strand board (OSB), the application of USG Levelrock™ Wood Primer to the subfloor is necessary to provide maximum bond between the underlayment and subfloor.

Concrete subfloors receiving USG Levelrock 3500/3500 Green underlayment systems must be cured properly (generally for a minimum of 28 days) prior to the underlayment installation. For on- or above-grade applications on concrete subfloors or concrete planks, measure the Moisture Vapor Emission Rate (MVER) using ASTM F1869. MVER should be below 5 lbs./1000 sq. ft./24 hrs. Contact USG for further information. Concrete subfloors should be treated properly with USG Levelrock™ Acrylic Concrete Primer according to USG recommendations. Refer to *USG Levelrock Floor Underlayment Finished Floor Installation Guidelines* (IG1457) for floor-covering installation.

Cracks in the existing concrete subfloor must be inspected to determine if the crack is due to typical concrete “shrink” or if it is a result of a structural movement. In the case of the latter, remediation of the crack must be addressed or eventually the crack will telegraph through USG Levelrock 3500 and 3500 Green floor underlayments. Repair all existing cracks in old and new concrete to minimize and control their ability to telegraph through the layer of USG Levelrock 3500 and 3500 Green floor underlayments. Remove the weak concrete along the length of the cracks by chiseling or other suitable means. Remove accumulated dust and debris from the crack cavities using a vacuum or other suitable means. Various cracks present in the concrete subfloor including shrinkage cracks must be filled with a suitable commercially available crack-fill epoxy adhesive designed for concrete flooring applications. To ensure superior resistance to crack growth, use injection epoxy crack-repair techniques per industry guidelines to repair cracks that are active or deep. Note that repair of existing cracks in the concrete subfloor only subdues, but does not completely prevent their ability to telegraph through USG Levelrock 3500 and 3500 Green floor underlayments. Growth of existing cracks or formation of new cracks in the concrete subfloor can lead to cracks telegraphing through USG Levelrock 3500 and 3500 Green floor underlayments. Respect existing expansion and control joints (see *Limitations* #6, pg. 2).

To minimize the effect of expansion and cracking on outside corners, use USG Levelrock perimeter isolation strip. See *USG Levelrock Brand Perimeter Isolation Strip Submittal* (IG1874) for further details.

For further details on installation requirements, specifications and the most up-to-date product information, please see usg.com or pourlevelrock.com.

PRODUCT DATA

Approximate Compressive Strength (aggregated) ASTM C472 (modified): 3500-4500 psi*

Approximate Dry Density (aggregated): 118-124 lbs./cu. ft.

NOTE: *Compressive strengths published herein were achieved under controlled laboratory conditions. Actual field results may differ due to environmental conditions, regional sand variations, inconsistent proportioning of field applied water, sand and USG Levelrock floor underlayment, as well as differences in mixing/pumping equipment.

TEST DATA

SOUND

USG has conducted a variety of sound tests on underlayment systems at NVLAP-accredited laboratories. These tests have been in conformance with ASTM E90 and E492. Consult USG publications IG1650 and SA305 for STC and IIC results on a variety of floor coverings meeting current code requirements.

UL DESIGNATION TYPE LRK

G524, G230, G516, G535, G551*, G553*, G556, G561, G562, G564*, G566, G587, G588, G591, J917, J919, J920, J924, J927, J931, J957, J958, J991, J994, L006, L201, L206, L208, L209, L210, L211, L212, L501, L502, L503, L504, L505, L506, L507, L508, L509, L510, L511, L512, L513, L514, L515, L516, L517, L518, L519, L520, L521, L522, L523, L524, L525, L526, L527, L528, L529, L530, L532, L533, L534, L535, L536, L537, L538, L539, L540, L541, L542, L543, L545, L546, L547, L549, L550, L551, L552, L556, L557, L558, L559, L562, L563, L564, L565, L568, L569, L570, L571, L573, L574, L577, L579, L581, L583, L585, L587, L588, L589, L590, L592, L593, M500, M501, M502, M503, M504, M505, M506, M508, M510, M511, M513, M515, M517*, M521*, M522*.

For the most up-to-date UL Designation Type LRK, contact your USG representative.

NOTE *UL Design requires greater minimum pour depths and compressive strengths and/or additional requirements. See individual UL Designs for specifics.

SUBMITTAL APPROVALS

Job Name	
Contractor	Date

PRODUCT INFORMATION

See usg.com or pourlevelrock.com for the most up-to-date product information.

LEED INFORMATION

For the most up-to-date information on LEED rating systems, project certification and the U.S. Green Building Council, please visit usgbc.org.

DANGER

Causes skin irritation. Causes serious eye damage. May cause an allergic skin reaction. May cause respiratory irritation. May cause cancer by inhalation of respirable crystalline silica. Do not handle until all safety precautions have been read and understood. Avoid breathing dust. Use only in a well-ventilated area, wear a NIOSH/MSHA-approved respirator. Wear protective gloves/protective clothing/eye protection. If swallowed, inhaled, or skin irritation occurs get medical attention. If on skin: Wash with plenty of water. If in eyes: Rinse cautiously with water for several minutes. Remove contact lenses and continue rinsing. Contaminated work clothing should not be allowed out of the workplace. Wash contaminated clothing before reuse. Dispose of in accordance with local, state, and federal regulations. For more information call Product Safety: 800-507-8899 or see the SDS at usg.com.

KEEP OUT OF REACH OF CHILDREN.

TRADEMARKS

The trademarks USG, DURÖCK, LEVELROCK, IT'S YOUR WORLD. BUILD IT., the USG logo, the design elements and colors and related marks are trademarks of USG Corporation or its affiliates.

XL Brands is a registered trademark of XL Brands, LLC.
LEED is a registered trademark of U.S. Green Building Council.

NOTICE

We shall not be liable for incidental or consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instruction or for other than the intended use. Our liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing to us within thirty (30) days from date it was or reasonably should have been discovered.

SAFETY FIRST!

Follow good safety/industrial hygiene practices during installation. Wear appropriate personal protective equipment. Read SDS and literature before specification and installation.

800 USG.4YOU
800 (874.4968)
usg.com
pourlevelrock.com
usgdesignstudio.com

Manufactured by
United States Gypsum Company
550 West Adams Street
Chicago, IL 60661

IG1448/rev. 6-15
© 2015 USG Corporation and/or
its affiliates. All rights reserved.
Printed in U.S.A.

USG 
IT'S YOUR WORLD. BUILD IT.™