

SHEETROCK® Brand Wall and Ceiling Spray Texture

Preparation	<p>Surface must be dry, clean, sound, and free of oil, grease, and efflorescence. Dull glossy surfaces; prime metal with a good rust-inhibitive primer. Concrete should be fully cured (at least 60 days after pouring). Grind plane differences and remove grinding dust and sludge. Fill and level with SHEETROCK® Brand DURABOND® Setting-Type or SHEETROCK® Brand EASY SAND™ Lightweight Setting-Type Joint Compound. Reinforce and conceal drywall joints using SHEETROCK® Brand Joint Tape and a United States Gypsum Company joint compound. Fill all fastener depressions with joint compound. Smooth surface scratches and scuffs. Correct plane irregularities, as these are accentuated by sharp, angular lighting. When prepared surfaces are dry and free of dust, apply SHEETROCK® Brand First Coat or a prime coat of good quality white interior latex flat wall paint with high solids content. Paint should be applied undiluted and allowed to dry before texturing.</p> <p>Note: Application of a prime coat is to equalize the surface porosity and to provide a uniform color. Primers are not intended to reduce sag potential or to prevent migratory stains or contaminants from leaching to the finished surface.</p>
Mixing	<p>Use heavy-duty drill fitted with a suitable mixing paddle; operate at not over 400 rpm. Excessive or high-speed mixing may produce voids in finished appearance. Thinning of texture with water will vary considerably, depending on the finished appearance desired and method of application to be employed. Mix until consistency is smooth and uniform. Do not mix with other materials in wet or dry form.</p> <p>Applicator should experiment with some of the mixed material prior to use, then adjust water proportions to suit the job. Over-thinning may cause poor bond, pinholes, and cracking.</p> <ul style="list-style-type: none">– For orange peel pattern, add up to 0.75 gal. (2.85 L) of water per 50 lbs. (22.7 kg) of texture.– For spatter and spatter/knockdown patterns: add up to 0.5 gal. (1.9 L) of water per 50 lbs. (22.7 kg) texture.
Coverage	<p>Use 300-700 sq. ft. per 50 lbs. (22.7 kg) as an estimated coverage rate. Actual coverage will vary depending on factors such as the type of texture design, the condition of the substrate surface, the amount of dilution of the product, application technique, and the uniformity of the coating.</p>
Application	<p>Texture must be evenly spread and free from runs, sags, and other blemishes. Allow texture to dry before applying paint. Maintain minimum air, texture material, and surface temperature of 55 °F (13 °C) within working area until texture is completely dry.</p>
Decoration	<p>This product is not washable unpainted and is not recommended as the final decoration. For final decoration, apply paint following manufacturer's directions.</p>
Cleanup	<p>Wash all equipment immediately after use with water containing household detergent.</p>

Trademarks

The following trademarks used herein are owned by United States Gypsum Company or a related company: DURABOND, EASY SAND, SHEETROCK.

Note

Products described here may not be available in all geographic markets. Consult your U.S. Gypsum Company sales office or representative for information.

Notice

We shall not be liable for incidental or consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instructions or for other than their intended use. Our liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing to us within thirty (30) days from the date it was or reasonably should have been discovered.

SAFETY FIRST!

Follow good safety practices. Read material safety data sheets and related literature on products before specification and/or installation.

