

ENVIRONMENTAL PRODUCT DECLARATION

USG Durock™ Brand Multi-Use Pro Green and Multi-Use Pro Green FR Floor Underlayments Baltimore, MD and Gypsum, OH



USG Durock™ Brand Multi-Use Pro Green and Multi-Use Pro Green FR Self-Leveling Underlayments are premium poured underlayment products with self-drying technology.

- Fast application, fast-setting allows for return of light trade traffic within hours
- Industry's most economical, highest compressive strength in class
- Ideal for wood-frame and multi-family construction
- UL designs available up to 2-hour fire rating
- Smooth, crack-resistant surface
- Helps maximize sound isolation between floors/units
- May assist in obtaining LEED® credits
- Applied by USG Durock™ Brand authorized applicators

USG Durock™ Brand Multi-Use Pro Green and Multi-Use Pro Green FR Self-Leveling Underlayments are fast applying engineered cementitious underlayments formulated and manufactured by USG for indoor use in multi-family, light-commercial and other wood-frame construction. These high-strength underlayments can be poured before drywall is installed, so they dry faster and help prevent mold by not exposing wallboard to high moisture levels. These engineered cementitious underlayments are also economical, as they can be applied at rates of up to 30,000 sq. ft. per day. They are formulated to provide typical compressive strengths from 2000 psi to 3200 psi at a ¾ in. minimum thickness over plywood subflooring, which meets requirements for multi-family and hotel/motel construction. USG Durock™ Brand Multi-Use Pro Green and Multi-Use Pro Green FR Self-Leveling Underlayments may assist in obtaining LEED® credits 5.1 and 5.2.

TRACI V2.1 ENVIRONMENTAL IMPACTS (CRADLE-TO-GATE)

Declared Unit – 1 metric tonne

| | Durock™ Brand Multi-Use Pro Green Baltimore, MD | Durock™ Brand Multi-Use Pro Green FR Gypsum, OH |
|--|--|--|
| Global Warming Potential (kg CO₂ eq.) | 1.72E+02 | 1.58E+02 |
| Ozone Depletion Potential (kg CFC-11 eq.) | 9.91E-08 | 1.38E-07 |
| Acidification Potential (kg SO₂ eq.) | 2.96E-01 | 3.98E-01 |
| Eutrophication Potential (kg N eq.) | 2.75E-02 | 4.35E-02 |
| Photochemical Ozone Creation Potential (kg O₃ eq.) | 5.94E+00 | 9.44E+00 |
| Abiotic Resource Depletion Potential Fossil Fuels (MJ, | 3.38E+02 | 2.87E+02 |

For over a century, sustainable practices have naturally been an inherent part of our business at USG. Today, they help shape the innovative products that become the homes where we live, the buildings where we work and the arenas where we play. From the product formulations we choose, to the processes we employ, USG is committed to designing, manufacturing, and distributing products that minimize overall environmental impacts and contribute toward a healthier living space. We believe that transparency of product information is essential for our stakeholders and EPDs are the next step toward an even more transparent USG. For additional information, visit usg.com, cgcinc.com and usgdesignstudio.com



ASTM INTERNATIONAL
WWW.ASTM.ORG
COPYRIGHT ©2014

ENVIRONMENTAL PRODUCT DECLARATION

USG Durock™ Brand Multi-Use Pro Green and
Multi-Use Pro Green FR Floor Underlayments
Baltimore, MD and Gypsum, OH

This declaration is an environmental product declaration (EPD) in accordance with ISO 14025 and ISO 21930; 2007. EPDs rely on Life Cycle Assessment (LCA) to provide information on a number of environmental impacts of products over their life cycle. Exclusions: EPDs do not indicate that any environmental or social performance benchmarks are met, and there may be impacts that they do not encompass. LCAs do not typically address the site-specific environmental impacts of raw material extraction, nor are they meant to assess human health toxicity. EPDs can complement but cannot replace tools and certifications that are designed to address these impacts and/or set performance thresholds – e.g. Type 1 certifications, health assessments and declarations, environmental impact assessments, etc. Accuracy of Results: EPDs regularly rely on estimations of impacts, and the level of accuracy in estimation of effect differs for any particular product line and reported impact. Comparability: EPDs are not comparative assertions and are either not comparable or have limited comparability when they cover different life cycle stages, are based on different product category rules or are missing relevant environmental impacts. EPDs from different programs may not be comparable.

| | | |
|---|---|--|
| DECLARATION NUMBER | EPD 137 | |
| PROGRAM OPERATOR | ASTM International – 100 Barr Harbor Drive, West Conshohocken, PA USA www.astm.org | |
| DECLARATION HOLDER | USG Corporation - 550 W. Adams St., Chicago, IL USA | |
| DECLARED PRODUCT | USG Durock™ Brand Multi-Use Pro Green Self-Leveling Underlayment USG Durock™ Brand Multi-Use Pro Green FR Self-Leveling Underlayment | |
| REFERENCE PCR | ASTM, Product Category Rules for Preparing an Environmental Product Declaration for: Portland Cement, Blended Hydraulic Cement and Masonry Cement, 2014 | |
| DATE OF ISSUE | 4/17/20 | |
| PERIOD OF VALIDITY | 5 Years | |
| CONTENTS OF THE DECLARATION | This EPD is complete and contains the following: <ul style="list-style-type: none"> • Product System Documentation • Life cycle Calculation Rules • Life Cycle Assessment Results • Further Information • References | |
| This declaration was independently verified in accordance with ISO 14025 and ISO 21930:2017 <input type="checkbox"/> INTERNAL <input checked="" type="checkbox"/> EXTERNAL | | Tim Brooke, ASTM International |
| This life cycle assessment was independently verified in accordance with ISO 14044 and the reference PCR by: | | Thomas P. Gloria, Industrial Ecology Consultants |

ENVIRONMENTAL PRODUCT DECLARATION

USG Durock™ Brand Multi-Use Pro Green and Multi-Use Pro Green FR Floor Underlayments Baltimore, MD and Gypsum, OH

1. Product System Documentation

1.1 Product Description and Product Identification

USG Durock™ Brand Multi-Use Pro Green Self-Leveling Underlayment is a fast applying engineered cementitious underlayment formulated and manufactured by USG for indoor use in multi-family, light-commercial and other woodframe construction. This high-strength underlayment can be poured before drywall is installed, so it dries faster and helps prevent mold by not exposing wallboard to high moisture levels. USG Durock™ Brand Multi-Use Pro Green Self-Leveling Underlayment engineered cementitious underlayment is also economical, as it can be applied at rates of up to 30,000 sq. ft. per day. They are formulated to provide typical compressive strengths from 2000 psi to 3200 psi at a ¾ in. minimum thickness over plywood subflooring, which meets requirements for multi-family and hotel/motel construction. USG Durock™ Brand Multi-Use Pro Green Self-Leveling Underlayment may assist in obtaining LEED® credits 5.1 and 5.2.

USG Durock™ Brand Multi-Use Pro Green FR Self-Leveling Underlayment is a fast-applying engineered cementitious underlayment formulated and manufactured by USG for indoor use in multi-family, light-commercial and other woodframe construction. Reinforced with fibers that improve impact strength, this underlayment can be poured before drywall is installed, so it dries dry faster and helps prevent mold by not exposing wallboard to high moisture levels. USG Durock™ Brand Multi-Use Pro Green FR self-leveling engineered cementitious underlayment is also economical, as it can be applied at rates of up to 30,000 sq. ft. per day. They are formulated to provide typical compressive strengths from 2000 psi to 3200 psi at a ¾ in. minimum thickness over plywood subflooring, which meets requirements for multi-family and hotel/motel construction. USG Durock™ Brand Multi-Use Pro Green FR Self-Leveling Underlayment may assist in obtaining LEED® credits 5.1 and 5.2.

1.2 Application

USG Durock™ Brand Multi-Use Pro Green and Multi-Use Pro Green FR products are high-quality, presanded, versatile cementitious floor underlayments for interior use in light-commercial and renovation construction. They can be easily applied over wood and concrete subfloors at a thickness of up to 3 inches. Its high compressive strength at low thicknesses provides superior underlayment performance for higher traffic areas. USG Durock™ Multi-Use Pro and Multi-Use Pro FR self-leveling underlayments are ideal substrates for a variety of floor coverings, ranging from vinyl to wood to tile. USG engineered cementitious underlayments are mixed with water at the job site to yield a lightweight underlayment with a smooth and monolithic surface.

1.3 Product Technical Data

The following technical construction data is relevant for the products covered by this EPD.

ENVIRONMENTAL PRODUCT DECLARATION

USG Durock™ Brand Multi-Use Pro Green and Multi-Use Pro Green FR Floor Underlayments

Baltimore, MD and Gypsum, OH

Table 1: Technical Specifications

| PHYSICAL AND MECHANICAL PROPERTIES | TEST STANDARD | APPROXIMATE VALUES STANDARD (METRIC) |
|------------------------------------|-----------------------------------|--|
| Approximate Compressive Strength | ASTM C109 (modified) ¹ | 2000 psi ² (13.8 MPa) at 24 hours |
| Approximate Dry Density | | 118-124 lbs./cu. ft. ² (1890-1986 kg/m ³) |
| Mixing Ratio | | 4.0–4.8 quarts (3.75–4.5 liters) of water per 50 lb. (22.7 kg) bag |
| Approximate Coverage | | 7 sq. ft. (0.65 m ²) per bag at 3/4 in. (19 mm) thickness |
| Approximate Flow Time | | 15-25 minutes |
| Approximate Final Set | ASTM C191 | 60–90 minutes ² |
| Approximate Light Foot Traffic | | 2 hours after set |
| Approximate Time to Flooring | | 15 hours (24 hours for wood) |
| Thickness Range | | 3/4 to 3 in. (without wire lath) |
| Surface pH Range | ASTM F710 | 11 |
| Packaging | | 50 lb. (22.7 kg) multiwall paper bags |

1. ASTM C109 modified refers to air drying as opposed to damp curing.

2. Results published herein were achieved under controlled laboratory conditions. Actual field results may differ due to environmental conditions, inconsistent proportioning of field-applied water and USG Durock™ Brand Multi-Use Pro Green Self-Leveling Underlayments and Multi-Use Pro Green FR, as well as differences in mixing/pumping equipment.

1.4 Product Composition

Table 2: Material Composition

| MATERIAL | USG DUROCK™ BRAND MULTI-USE PRO GREEN SELF- LEVELING UNDERLAYMENT BALTIMORE / GYPSUM | USG DUROCK™ BRAND MULTI-USE PRO GREEN FR SELF-LEVELING UNDERLAYMENT BALTIMORE / GYPSUM |
|------------------|---|--|
| Cement | 99.1% / 96.2% | 98.8% / 98.4% |
| Filler | 0.0% / 0.0% | 0.0% / 0.0% |
| Additives | 0.9% / 3.8% | 1.2% / 1.6% |
| Sum | 100.0% / 100.0% | 100.0% / 100.0% |

Cement components may include stucco, hydrocal and Portland cement. Additives may include plasticizers, retarders, accelerators, defoamers and additional binders.

ENVIRONMENTAL PRODUCT DECLARATION

USG Durock™ Brand Multi-Use Pro Green and Multi-Use Pro Green FR Floor Underlayments Baltimore, MD and Gypsum, OH

1.5 Product Manufacture

The manufacture of USG Durock™ Brand Multi-Use Pro Green Self-Leveling Underlayment and Multi-Use Pro Green FR consists of the blending of the dry ingredients followed by packaging into multi-wall paper bags. The finished product is then stacked on wooden pallets and wrapped with a plastic film.



1.6 Environment and Health During Manufacturing

USG has led the building sector's effort in developing and supplying sustainable construction materials. Today, sustainability is integrated into the design and manufacture of every wall, ceiling, and flooring product. As both a producer and a buyer of raw materials, we have a responsibility to extensively review and select each material we use. Each decision we make is based on careful consideration of environmental and safety effects over time. Raw materials used in our products are carefully selected and go through a screening procedure. Incoming raw materials are tested for contaminants by an internal lab and third-party labs for consideration of use and worker, environmental, and end-user exposure. This due diligence helps to ensure our products are safe to handle in our manufacturing plants and on job sites while having minimal impact on occupant health and indoor and outdoor environments.

1.7 Packaging

USG floor underlayments are packaged in 50 lb. multi-wall paper bags. Both the production and disposal of these packaging materials was modeled in this study.

1.8 Reference Service Life

The Reference Service Life is considered not to be relevant for this cradle-to-gate study.

1.9 Extraordinary Effects

None

2. LCA Calculation Rules

2.1 Declared Unit

The declared unit for this LCA study is one metric tonne of product. This declared unit is consistent with the PCR.

Table 3: Declared Unit

| NAME | USG DUROCK™ BRAND MULTI-USE PRO GREEN SELF-LEVELING UNDERLAYMENT AND MULTI-USE PRO GREEN FR |
|----------------------|---|
| Declared Unit (kg) | 1,000 kg |
| Declared Unit (lbs.) | 2205 lbs. |

2.2 System Boundary

This EPD represents a “cradle-to-gate” LCA analysis for USG Durock™ Brand Multi-Use Pro Green Self-Leveling Underlayment and Multi-Use Pro Green FR. It covers all the production steps from raw material extraction (i.e., the cradle) to packaged bags of product at the factory gate.

ENVIRONMENTAL PRODUCT DECLARATION

USG Durock™ Brand Multi-Use Pro Green and Multi-Use Pro Green FR Floor Underlayments Baltimore, MD and Gypsum, OH

2.3 Estimates and Assumptions

These floor underlayment products are USG products with well-defined formulations, energy inputs and raw material transport distances. No significant assumptions were required. All material and energy inputs were accounted for as were the raw material transportation mode and distances. Additional data limitations included the use of proxy processes rather than actual supplier generated primary data. This would include such processes as Portland cement, which is representative of US-produced Portland cement but may not necessarily be representative of USG's particular Portland cement supplier. In addition, the data is limited in that the primary data was collected during the 2017 year and changes in operations may increase/decrease impacts in the future. Other data limitations include the use of secondary data sets instead of primary data for upstream and downstream processes, local impacts vs. global impacts, possible impacts vs. actual impacts, inherent uncertainty in the data sets, accuracy and precision of impact assessment methodology, etc.

2.4 Cut-off Criteria

All inputs and outputs to a (unit) process were included in the calculation for which data is available.

In case of insufficient input data or data gaps for a unit process, the cut-off criteria was 1% of renewable and non-renewable primary energy usage and 1% of the total mass of that unit process. The total neglected input flows did not exceed 5% of energy usage and mass.

As such, some minor additives fell well below the cut-off criteria and were therefore not included in this study.

2.5 Background Data

All background was sourced from critically reviewed GaBi databases.

2.6 Data Quality

The LCA model was created using the GaBi ts software. Specific comments related to data quality requirements cited in ISO 14025 Section 4.2.3.6.2 include the following.

Temporal: In the case of USG Durock™ Brand Multi-Use Pro Green Self-Leveling Underlayment and Multi-Use Pro Green FR production, the LCI data was collected from the Baltimore, MD and Gypsum, OH plants for the 2017 production year.

Geographical: Where possible, all processes were chosen as being representative of US manufacturing processes. Specifically, this would include electricity generation. The specific process selected for electricity generation was chosen to be specific to the specific region in the US using the updated eGRID system.

Technical: The data selected for this study is specific to the technology used in the preparation of the various raw materials.

Precision: The raw material usage amounts for panel were derived from plant data. They are representative of actual usage for the 2017 calendar year.

Completeness: All significant raw material flows used in the production of USG Durock™ Brand Multi-Use Pro Green Self-Leveling Underlayment and Multi-Use Pro Green FR have been modeled.

Representative: Where possible all the data sets were selected to be representative of US-based production, are less than 10 years in age and are representative of the technology being employed.

ENVIRONMENTAL PRODUCT DECLARATION

USG Durock™ Brand Multi-Use Pro Green and Multi-Use Pro Green FR Floor Underlayments

Baltimore, MD and Gypsum, OH

Consistency: All the manufacturing processes were modeled in a consistent manner throughout this study in accordance with the goal and scope definitions.

Reproducibility: The information contained in this study, including raw material, energy and transportation distance inputs, have been fully documented in the LCA report.

Sources of Data: The sources for the processes used in this study have been fully provided in the LCA report and are representative of the material and energy sources used in actual production.

Uncertainty: The relative uncertainty associated with this study has been minimized. No significant assumptions have been made.

2.7 Period under Review

All raw material and energy inputs are for the 2017 calendar year.

2.8 Allocation

No allocations were required for this LCA study.

2.9 Comparability

A comparison or evaluation of EPD data is only possible if all data sets to be compared are 1) created according to EN 15804 and 2) are considered in a whole building context or utilize identical defined use stage scenarios. Comparisons are only allowable when EPDs report cradle-to-grave information using a functional unit. Refer to section 5.3 of EN 15804 for further information. Comparison of the environmental performance of panels using EPD information shall be based on the product's use and impacts at the building level, and therefore EPDs may not be used for comparability purposes when not considering the building energy use phase as instructed under this PCR. Full conformance allows EPD comparability only when all stages of the life cycle have been considered. However, variations and deviations are possible

3. Life Cycle Assessment Results

Table 4: Description of the system boundary modules

| PRODUCT STAGE | | | CONSTRUCTION PROCESS STAGE | | USE STAGE | | | | | | | END OF LIFE STAGE | | | | BENEFITS AND LOADS BEYOND THE SYSTEM BOUNDARIES |
|---------------------|-----------|---------------|-----------------------------|------------------|-----------|-------------|--------|-------------|---------------|------------------------|-----------------------|-------------------|-----------|------------------|----------|---|
| Raw Material Supply | Transport | Manufacturing | Transport From Gate to Site | Assembly/Install | Use Stage | Maintenance | Repair | Replacement | Refurbishment | Operational Energy Use | Operational Water Use | Deconstruction | Transport | Waste Processing | Disposal | Reuse, Recovery, Recycling Potential |
| A1 | A2 | A3 | A4 | A5 | B1 | B2 | B3 | B4 | B5 | B6 | B7 | C1 | C2 | C3 | C4 | D |
| X | X | X | MND | MND | MND | MND | MND | MND | MND | MND | MND | MND | MND | MND | MND | MND |

ENVIRONMENTAL PRODUCT DECLARATION

USG Durock™ Brand Multi-Use Pro Green and Multi-Use Pro Green FR Floor Underlayments

Baltimore, MD and Gypsum, OH

Table 5: Acronym Key

| ABBREVIATION | PARAMETER | UNIT |
|--|---|------------------------|
| Life Cycle Impact Assessment Indicators | | |
| GWP | Global Warming Potential | kg CO ₂ eq. |
| ODP | Ozone Depletion Potential | kg CFC-11 eq. |
| AP | Acidification Potential | kg SO ₂ eq. |
| EP | Eutrophication Potential | kg N eq. |
| POCP | Photochemical ozone creation potential | kg O ₃ eq. |
| ADP | Abiotic resource depletion potential – fossil fuels | MJ, LHV |
| Resource Use Parameters | | |
| PERE | Use of renewable primary energy excluding renewable primary energy resources used as raw materials | MJ, LHV |
| PERM | Use of renewable primary energy resources used as raw materials | MJ, LHV |
| PERT | Total use of renewable primary energy resources (primary energy and primary energy resources used as raw materials) | MJ, LHV |
| PENRE | Use of non-renewable primary energy excluding non-renewable primary energy resources used as raw materials | MJ, LHV |
| PENRM | Use of non-renewable primary energy resources used as raw materials | MJ, LHV |
| PENRT | Total use of non-renewable primary energy resources (primary energy and primary energy resources used as raw materials) | MJ, LHV |
| SM | Use of secondary materials | kg |
| RSF | Use of renewable secondary fuels | MJ, LHV |
| NRSF | Use of non-renewable secondary fuels | MJ, LHV |
| FW | Net use of fresh water | m ³ |
| Waste Parameters | | |
| HWD | Disposed-of-hazardous waste | kg |
| NHWD | Disposed-of non-hazardous waste | kg |
| RWD | Radioactive Waste Disposed | kg |
| Output Flow Parameters | | |
| CRU | Components for reuse | kg |
| MFR | Materials for recycling | kg |
| MER | Materials for energy recovery | kg |
| EE | Exported energy | MJ |

ENVIRONMENTAL PRODUCT DECLARATION

USG Durock™ Brand Multi-Use Pro Green and Multi-Use Pro Green FR Floor Underlayments Baltimore, MD and Gypsum, OH

3.1 Life Cycle Impact Assessment Results

Table 6: LCA Results for 1 Tonne of USG Durock™ Brand Multi-Use Pro Green Self-Leveling Underlayment

| TRACI v2.1 | UNITS | A1-A3 BALTIMORE | A1-A3 GYPSUM |
|------------|------------------------|-----------------|--------------|
| GWP 100 | kg CO ₂ eq. | 1.72E+02 | 1.58E+02 |
| ODP | kg CFC-11 eq. | 9.91E-08 | 1.38E-07 |
| AP | kg SO ₂ eq. | 2.96E-01 | 3.98E-01 |
| EP | kg N eq. | 2.75E-02 | 4.35E-02 |
| POCP | kg O ₃ eq. | 5.94E+00 | 9.44E+00 |
| ADP | MJ | 3.38E+02 | 2.87E+02 |

Table 7: LCA Results for 1 Tonne of USG Durock™ Brand Multi-Use Pro Green FR Self-Leveling Underlayment

| TRACI v2.1 | UNITS | A1-A3 BALTIMORE | A1-A3 GYPSUM |
|------------|------------------------|-----------------|--------------|
| GWP 100 | kg CO ₂ eq. | 1.81E+02 | 1.91E+02 |
| ODP | kg CFC-11 eq. | 9.91E-08 | 1.38E-07 |
| AP | kg SO ₂ eq. | 3.12E-01 | 4.51E-01 |
| EP | kg N eq. | 2.97E-02 | 4.95E-02 |
| POCP | kg O ₃ eq. | 6.26E+00 | 1.06E+01 |
| ADP | MJ | 3.70E+02 | 3.94E+02 |

ENVIRONMENTAL PRODUCT DECLARATION

USG Durock™ Brand Multi-Use Pro Green and Multi-Use Pro Green FR Floor Underlayments

Baltimore, MD and Gypsum, OH

3.2 Life Cycle Inventory Results

Table 8: Resource Use for 1 Tonne of USG Durock™ Brand Multi-Use Pro Green Self-Leveling Underlayment

| PARAMETER | UNITS | A1-A3 BALTIMORE | A1-A3 GYPSUM |
|-----------|----------------|-----------------|--------------|
| PERE | MJ | 3.54E+02 | 3.72E+02 |
| PERM | MJ | 0.00E+00 | 0.00E+00 |
| PERT | MJ | 3.54E+02 | 3.72E+02 |
| PENRE | MJ | 2.70E+03 | 2.33E+03 |
| PENRM | MJ | 0.00E+00 | 0.00E+00 |
| PENRT | MJ | 2.70E+03 | 2.33E+03 |
| SM | MJ | 9.76E+02 | 9.65E+02 |
| RSF | MJ | 0.00E+00 | 0.00E+00 |
| NRSF | MJ | 0.00E+00 | 0.00E+00 |
| FW | m ³ | 4.27E-01 | 3.02E-01 |

Table 9: Resource Use for 1 Tonne of USG Durock™ Brand Multi-Use Pro Green FR Self-Leveling Underlayment

| PARAMETER | UNITS | A1-A3 BALTIMORE | A1-A3 GYPSUM |
|-----------|----------------|-----------------|--------------|
| PERE | MJ | 3.54E+02 | 4.01E+02 |
| PERM | MJ | 0.00E+00 | 0.00E+00 |
| PERT | MJ | 3.54E+02 | 4.01E+02 |
| PENRE | MJ | 2.70E+03 | 3.14E+03 |
| PENRM | MJ | 0.00E+00 | 0.00E+00 |
| PENRT | MJ | 2.70E+03 | 3.14E+03 |
| SM | MJ | 9.73E+02 | 9.62E+02 |
| RSF | MJ | 0.00E+00 | 0.00E+00 |
| NRSF | MJ | 0.00E+00 | 0.00E+00 |
| FW | m ³ | 4.27E-01 | 4.61E-01 |

ENVIRONMENTAL PRODUCT DECLARATION

USG Durock™ Brand Multi-Use Pro Green and Multi-Use Pro Green FR Floor Underlayments Baltimore, MD and Gypsum, OH

Table 10: Output Flows and Waste Categories for 1 Tonne of USG Durock™ Brand Multi-Use Pro Green Self-Leveling Underlayment

| PARAMETER | UNITS | A1-A3 BALTIMORE | A1-A3 GYPSUM |
|-----------|-------|-----------------|--------------|
| HWD | kg | 1.38E-03 | 2.03E-03 |
| NHWD | kg | 1.24E+01 | 1.18E+01 |
| RWD | kg | 2.37E-02 | 1.94E-02 |
| CRU | kg | 0.00E+00 | 0.00E+00 |
| MFR | kg | 0.00E+00 | 0.00E+00 |
| MER | kg | 0.00E+00 | 0.00E+00 |
| EE | MJ | 0.00E+00 | 0.00E+00 |

Table 11: Output Flows and Waste Categories for 1 Tonne of USG Durock™ Brand Multi-Use Pro Green FR Self-Leveling Underlayment

| PARAMETER | UNITS | A1-A3 BALTIMORE | A1-A3 GYPSUM |
|-----------|-------|-----------------|--------------|
| HWD | kg | 1.38E-03 | 2.03E-03 |
| NHWD | kg | 1.24E+01 | 1.23E+01 |
| RWD | kg | 2.37E-02 | 3.27E-02 |
| CRU | kg | 0.00E+00 | 0.00E+00 |
| MFR | kg | 0.00E+00 | 0.00E+00 |
| MER | kg | 0.00E+00 | 0.00E+00 |
| EE | MJ | 0.00E+00 | 0.00E+00 |

ENVIRONMENTAL PRODUCT DECLARATION

USG Durock™ Brand Multi-Use Pro Green and Multi-Use Pro Green FR Floor Underlayments Baltimore, MD and Gypsum, OH

3.3 LCA Interpretation

The LCA results for the production of USG Durock™ Brand Multi-Use Pro Green Self-Leveling Underlayment and Multi-Use Pro Green FR were dominated by raw material contributions particularly cement. For example, total cement usage was responsible for 85% of the global warming impact in a cradle-to-gate analysis for Baltimore USG Durock™ Brand Multi-Use Pro Green Self-leveling Underlayment.

4. Further Information

4.1 VOC Emissions

USG Durock™ Brand Multi-Use Pro Green Self-Leveling Underlayment and Multi-Use Pro Green FR achieved GREENGUARD Gold Certification and qualifies as a "Low Emitting" material per California Department of Public Health CDPH/EHLB/Standard Method (CA Section 01350) for school classroom, and private office modeling scenarios, and meets USGBC's LEED® v4 emission requirements.

5. References

LCA Report

A Cradle-to-Gate (A1-A3) Life Cycle Assessment for USG Flooring Products Produced at Baltimore, MD and Gypsum, OH, Baltimore, MD and Gypsum, OH; 3/18/20. USG.

Product PCR

ASTM, Product Category Rules for Preparing an Environmental Product Declaration for: Portland Cement, Blended Hydraulic Cement and Masonry Cement, 2014

SUSTAINABILITY REPORTING STANDARDS

EN 15804: 2012-04 - Sustainability of construction works — Environmental Product Declarations — Core rules for the product category of construction product.

ISO 14025: 2006 - Environmental labels and declarations — Type III environmental declarations — Principles and procedures

ISO 14040: 2006 - Environmental management – Life cycle assessment – Principles and framework

ISO 14044:2006 - Environmental management – Life cycle assessment – Requirements and guidelines

ISO 14046:2013 - Environmental management- Water footprint- Principles, requirements and guidelines

ISO 15392:2008 - Sustainability in building construction- General principles

ISO 15686-1:2011 - Buildings and constructed assets- Service life planning- Part 1: General principles

ISO 15686-2:2008 - Buildings and constructed assets- Service life planning Part 2: Service life prediction procedures

ISO 15686-7:2008 - Buildings and constructed assets- Service life planning Part 7: Performance evaluation for feedback of service life data from practice

ISO 15686-8:2008 - Buildings and constructed assets- Service life planning Part 8: Reference service life and service life estimation

ISO 21930: 2007 - Sustainability in building construction -- Environmental declaration of building products



ASTM INTERNATIONAL
WWW.ASTM.ORG
COPYRIGHT ©2014