

USG DUROCK™ BRAND PROFLOW™ SELF-LEVELING UNDERLAYMENT

Technical Data	USG Durock™ Brand ProFlow™ Self-Leveling Underlayment ¹	CMP Specialty Products LP-1 ²
Composition	Gypsum Cement Blend	Hybrid Gypsum Blend
Thickness	Featheredge to 3 in. (.76 mm) ³ (any thickness in small, well-defined areas)	1/4 in. (6 mm) up to any thickness
Compressive Strength	6,000 – 8,000 psi (41.4 – 55.2 MPa)	5,000 psi (34.5 MPa)
Mixing Ratio Per Bag (Water)	3.6 – 4.8 quarts (3.4 – 4.5 L)	5 quarts (4.73 L)
Flow Time⁴ at 70 °F (21 °C)	15 minutes	20 minutes
Walkable⁴	3 hours	1 hour
Finish Floor Application⁴	2 – 5 days	2 days (minimum)
Final Usage	Underlayment and wear surface with appropriate coating	Underlayment
Coverage at 1/4 in. (6 mm)	22 sq. ft. (2.04 m ²)	22 sq. ft. (2.04 m ²)
Self-Leveling	Yes	Yes
GREENGUARD Gold Certification	Yes	No
Website	usg.com	cmpsp.com

Surface Preparation	USG Durock™ Brand ProFlow™ Self-Leveling Underlayment ¹	CMP Specialty Products LP-1 ²
Concrete Slab Cure Minimum	28 days	28 days
Building Enclosed	Yes	Yes
Remove Mud, Oil, Grease and Other Contaminating Factors	Yes	Yes
Shot Blasting or Scarification	Not required for most applications	Not required for most applications

PRODUCT INFORMATION

See usgperformanceflooring.com for the most up-to-date product information.

GREENGUARD INFORMATION

GREENGUARD Certified products are certified to GREENGUARD standards for low chemical emissions into indoor air during product usage. For more information, visit ul.com/gg.

TRADEMARKS

The trademarks USG, DUROCK, PROFLOW, IT'S YOUR WORLD. BUILD IT., the USG logo, the design elements and colors, and related marks are trademarks of USG Corporation or its affiliates.

NOTE

The information in this document is subject to change without notice. USG Corp. assumes no responsibility for any errors that may inadvertently appear in this document. Consult your USG Company sales office or representative for information.

NOTICE

We shall not be liable for incidental or consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instruction or for other than the intended use. Our liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing to us within thirty (30) days from date it was or reasonably should have been discovered.

SAFETY FIRST!

Follow good safety/industrial hygiene practices during installation. Wear appropriate personal protective equipment. Read SDS and literature before specification and installation.

NOTES:

1. Data taken from *USG Durock™ Brand ProFlow™ Self-Leveling Underlayment Submittal* (CB579/7-15).
2. Competitive product data taken from CMP Specialty Products (A Division of CGM, Inc.) LPI Technical Datasheet (Rev. 2-15).
3. Contact USG when pouring thicknesses exceeding 1 in. (25 mm).
4. Warmer temperatures can decrease working/dry time, and cooler temperatures and high humidity can increase working/dry time on both products.

800 USG.4YOU
800 (874.4968)
usgperformanceflooring.com
usg.com

United States Gypsum Company
550 West Adams Street
Chicago, IL 60661

CB5222-USA-ENG/9-18
© 2018 USG Corporation and/or its affiliates. All rights reserved.
Printed in U.S.A.